



No. 0307/8889

To C EXTRA ENGINEERING CO., LTD.

The Department of Science Service presents the test report for the sample named "XPE FOAM" Laboratory No. L62/02497.1 as the total of 1 sample with reference to the request No. L62/02497 Dated 15 May 2019

Enclosed here with the following result avails for your acknowledgement.



Physics and Engineering Program

Tel. 0 2201 7130

Fax. 0 2201 7127

E-mail : physics@dss.go.th



TEST REPORT

Sample's name
XPE FOAM

Mark / Brand

Laboratory No.
L62/02497.1


Test Results

Chemical resistance

Acetic acid 5%	not changed
Sulfuric acid 30%	not changed
Hydrochloric acid 10%	not changed
Sodium chloride solution 10%	not changed
Ammonia 10%	not changed
Nitric acid 10%	not changed

Customer's name C EXTRA ENGINEERING CO., LTD.
 Customer's address 30/22 Moo 3 T. Rahaeng, A. Ladlumkaew, Pathumthani 12140
 Sample's description Grey PE foam with thickness 5 cm width 75 cm and length 97 cm
 Test date 15-23 May 2016
 Test method ASTM D 1308-02 (Reapproved 2013) Spot test, covered for 24 h.


Approved by



(Mrs. Premjai Athakitkarnka)

Scientist, Senior Professional Level

Reported by



(Miss Somjit Tungchaiwattana)

Scientist, Professional Level

This report is only valid for the sample received. The above statement is not intended for advertising purposes and shall not be reproduced or shall not manifest partially without the written permission of the Department of Science Service.

Department of Science Service, Ministry of Science and Technology
 Rama VI Road, Ratchathewi, Bangkok 10400, Thailand