



No. 0307/ 17692

To C Extra Trading Co., Ltd.

The Department of Science Service presents the test report for the sample named "Cross-linked Polyethylene Foam" Laboratory No. L63/08345.1 as the total of 1 sample with reference to the request No L63/08345 dated 14 September 2020.

Enclosed herewith the following result avails for your acknowledgement.

Department of Science Service

10 November 2020



Division of Engineering Materials

Tel. 0 2201 7130

Fax 0 2201 7127

E-mail : physics@dss.go.th



TEST REPORT

Sample's name

Cross-linked Polyethylene
Foam

Mark / Brand

C cool

Laboratory No.

L63/08345.1

Test Results

Dimensional stability : Air-circulating oven aging at 104°C for 7 days.

Change in length, %

- Machine direction	-1.3
- Transverse direction	-4.0

Customer's name

C Extra Trading Co., Ltd.

Customer's address

30/22 Moo 3, Rahaeng, Lat Lum Kaeo, Pathum Thani 12140

Sample's description

Foam sheet

Test date

26 October 2020 - 2 November 2020

Test method

ASTM C 534/C 534M-14

Approved by

Anon Pomprasit
(Mr. Anon Pomprasit)

Scientist, Senior Professional Level

Reported by

Saowaluck Ukrisdawithid
(Ms. Saowaluck Ukrisdawithid)

Scientist, Senior Professional Level

This report is only valid for the sample received. The above statement is not intended for advertising purposes and shall not be partially reproduced or manifested without the written permission from the Department of Science Service.

Department of Science Service, Ministry of Higher Education Science Research and Innovation
Rama VI Road, Ratchathewi, Bangkok 10400, Thailand