



No. 0307/ 8888

To P&I (Thailand) Co., Ltd.

The Department of Science Service presents the test report for the sample named "XPE FOAM" Laboratory No. L59/03961.1 as the total of 1 sample with reference to the request No. L59/03961 dated 26 July 2016.

Enclosed here with the following result avails for your acknowledgement.

Department of Science Service



Physics and Engineering Program

Tel. 0 2201 7130

Fax. 0 2201 7127

E-mail : physics@dss.go.th



TEST REPORT

Sample's name
XPE FOAM

Mark / Brand

Laboratory No.
L59/03961.1

Test Results

Tensile strength, N/cm ²	34.6
Elongation at break, %	116
Tear strength, N/cm	20.6
Permanent set in compression, %	25.5

Customer's name P&I (Thailand) Co., Ltd.
 Customer's address 209/164 Moo 3 T. Bung A. Sriracha Chonburi 20230 Thailand
 Sample's description Grey PE foam with thickness 5 cm width 75 cm and length 97 cm
 Test date 2 August – 5 August 2016
 Test method JIS K 6767 (1976)

Approved by

Premjai Athakithkarnka

(Mrs.Premjai Athakithkarnka)

Scientist, Senior Professional Level

Reported by

Somjit Tungchaiwattana

(Miss Somjit Tungchaiwattana)

Scientist, Professional Level

This report is only valid for the sample received. The above statement is not intended for advertising purposes and shall not be reproduced or shall not manifest partially without the written permission of the Department of Science Service.